

# SX300NA

## HIGH PERFORMANCE LATEX UNDERLAYMENT



### KEY BENEFITS SUMMARY

- Water resistant: can be used for pre-smoothing
- Excellent adhesion to a wide range of common flooring substrates, including: concrete, sand/cement screeds, flooring grade asphalt, TREMCO surface DPM's, etc.
- Self priming on most surfaces
- Short setting and cure time, facilitating fast track programs and minimising disruption
- Low odour and protein free

### PRODUCT INFORMATION

#### Description

SX300 NA is a two part general purpose smoothing underlayment for interior applications.

#### Usage/Purpose

SX300 NA is specifically designed for the preparation and smoothing of interior subfloors prior to the application of a liquid applied damp proof membrane and receiving a floor covering.

#### Colour

Part A: Grey powder  
Part B: White liquid

#### Packaging

Part A: 22 kg plastic lined reinforced paper sack  
Part B: 4.65 kg polythene jerry can

#### Standards

All aspects of the installation must be in accordance with the requirements of BS 8204, BS 8203 (Installation of Resilient Floor Coverings) or BS 5325 (Installation of Textile Floor Coverings) and supplementary specifications.

#### Accreditations

- Complies with HTM 61 requirements

#### Declaration of Performance

SX300NA-20140702

#### Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. Do not breathe dust. Contains Portland cement. Skin contact with wet cement, fresh concrete or mortar may cause irritation, dermatitis or burns. For full recommendation, refer to safety data sheet.

#### Preparation

- Ensure all surfaces to be coated are clean, dry, frost free and free from grease, oil, dirt, dust, loose friable material and any other contaminants (coating, laitance, etc).

- Any surface hardener or curing compounds should be thoroughly removed prior to the application of SX300 NA. For full details of surface preparation contact Tremco CPG UK Limited Technical Services.

#### Priming

In some case it may be necessary to prime with CS150 Acrylic Primer for porous substrates or CS100 Epoxy Primer for non-porous substrates. Always check with the Tremco CPG UK Limited Technical Services.

#### Mixing

Gradually add Part A to Part B, continually mixing with a slow speed drill and paddle. Mix the contents for 2 - 3 minutes to obtain uniformity in colour and consistency.

#### Application

SX300 NA should be applied directly after mixing by pouring a ribbon of material along the wet edge and then trowelled to form a smooth, even finish. The effective use of spike rolling can reduce visible trowel marks.

#### Protection on Completion

Ensure the screed is not subject to draughts during the first 6 hours of curing as this may lead to cracking and crazing. Tape up doorways with polythene to prevent air movement.

Prevent contamination by following trades (e.g. plastering), including water spillage.

#### Cleaning

Immediately after use all tools and equipment should be cleaned with water. Cured material can be removed mechanically or by acid etching.

#### Please Note

Not suitable for use in areas that may be subject to high point loading.

#### Health & Safety Precautions

Safety data sheet must be read and understood before use.

#### Contract Application

Tremco CPG UK Limited has a network of nationwide approved installers and provides full technical assistance on specific site applications.

# SX300NA

## HIGH PERFORMANCE LATEX UNDERLAYMENT



### Availability

Direct from Tremco CPG UK Limited (see back of leaflet for address and telephone details), or via local and national distributors.

### Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

### Guarantee/Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco CPG UK Limited Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

### TECHNICAL DATA

PROPERTY	RESULT
Composition	Cementitious powder and liquid latex dispersion
Pot Life (at 20°C)	20 minutes
Compressive Strength	After 28 days approx. 21.9 N/mm <sup>2</sup>
Tensile Strength	28 days 1.4 N/mm <sup>2</sup>
Coverage	Thicknesses of 6 mm to feather edge can be applied dependant on surface profile. An average thickness of 3 mm will provide a coverage rate of 5 m <sup>2</sup> per mix Thicknesses of 8 mm to 30 mm can be achieved by incorporating an equal volume of 3 mm granite chippings This will depend on the condition of the substrate and method of preparation (please refer to Tremco CPG UK Limited Technical Department)
Cure Time (at 20°C)	Between 2 - 4 hours for foot traffic and 8 - 12 hours for application of damp proof membrane, floor covering and loading
Storage	Store in dry, shaded conditions between +10°C and +35°C
Shelf Life	6 months when stored as recommended in original unopened packaging High temperatures and humidity will lead to a reduced shelf life

Tremco CPG UK Limited - A Company approved to:



Tremco CPG UK Limited  
Coupland Rd, Hindley Green, Wigan WN2 4HT  
United Kingdom  
Tel: +44 (0)1942 251400  
Email: hello@tremcocpg.com



2021-03