

# **GRIP E946 EPOXY**

# TWO-COMPONENT, SOLVENT-FREE, WATER DISPERSIBLE PRIMER

Date: 22 September 2021 Fact Sheet No.: TDS00850

## YOUR SMART ADVANTAGES

- Solvent-free
- Excellent adhesion
- Ideal for use when applying Bostik smoothing compound above 10mm

#### **USES**

Bostik GRIP E946 EPOXY is a solvent-free, two-component, water dispersible epoxy primer containing exact quantities of resin and hardener ready for mixing. Curing is by chemical reaction, producing a semi-gloss film finish. The primer is coloured to identify coated areas.

Bostik GRIP E946 EPOXY can be used as a primer/bonding agent prior to the application of any of the Bostik range of smoothing compounds. It can be used on all smooth and dense surfaces, power floated concrete, ceramic tiles, quarry tiles, terrazzo, rigid metal, asphalt and surface membranes.

It may also be used as a barrier primer on anhydrite (calcium sulphate) screeds, prior to the application of cementitious materials. For further information, please contact Technical Services.

PRODUCT CHARACTERISTICS	
Colour	White
Form	Liquid paste
Specific Gravity	1.0 approx.
Composition	Resin mix
Product Codes	30620597 6kg bucket containing part A & B
Storage/Shelf Life	Store and transport securely in an upright position. Ensure the lid is secure. Store for up to 12 months

from date of manufacture in original,
unopened packaging in cool, dry
conditions within the temperature
range +5°C to +25°C and out of direct
sunlight. Protect from frost.

TYPICAL PERFORMANCE DATA (Approx.)		
Application Temperature	+5°C to +40°C	
Coverage	Smooth surfaces: 50m² to 60m²	
	Barrier primer for calcium sulphate screeds: Up to 150m²	
	(depending on the smoothness of the floor surface & application technique)	
Drying Times	2 to 6 hours, but do not leave for longer than 24 hours (depending ambient temperatures)	
Cleaning	Clean tools and equipment with warm water immediately after use. Use white spirit if the material has dried	

#### **DIRECTIONS FOR USE**

IMPORTANT: Before using Bostik GRIP E946 EPOXY, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of installation should comply with the latest editions of:

- BS 8102 Code of Practice for protection of structures against water from the ground.
- BS 5325 Code of Practice for installation of textile floor coverings.
- BS 8203 Code of Practice for installation of resilient floor coverings.
- BS 8201 Code of Practice for installations of for

flooring of timber, timber products and wood based panel products.

#### **PREPARATION**

#### Subfloor:

- Ensure the subfloor is sound, clean, dry and of adequate tensile and compressive strength, free from loose material, laitance, cracks and structural defects. All contaminants, including surface hardeners and additives that may hinder adhesion must be removed. It should also have an effective structural damp-proof membrane and be suitably dry.
- 2. The subfloor should be tested in accordance with British Standards. A reading of 75% RH or less confirms that the subfloor is satisfactorily dry.
- 3. Where this has not been achieved, the use of a suitable Bostik surface membrane will suppress residual moisture in a power floated concrete slab or sand/cement screed, provided a base DPM has been incorporated. Please refer to the relevant data sheets for full information. For anhydrite screeds contact Technical Services.

#### MIXING

# As a primer/bonding agent for difficult substrates, or thick applications of smoothing compounds:

- 4. Add hardener B to resin A, and mix the two components together using an electric drill and propeller blade until a completely uniform colour is obtained.
- The components should not be mixed together until application is ready to start, and should be applied as soon as mixing has been completed. Poorly mixed or unmixed material will not harden.

## As a barrier primer for calcium sulphate screeds:

- 6. When being used as a barrier primer over dry anhydrite screeds, the product should initially be mixed as above.
- Decant the mixed material into a larger container and slowly add, whilst still mixing a further 5 litres of clean, cold water.
- 8. Once thoroughly mixed (typically a minimum of 2 minutes), the primer should be applied to a dust and laitance free screed by either brush or roller. Poorly mixed or unmixed material will not harden.

#### **APPLICATION**

 Apply the mixed material by brush or lambswool roller, ensuring that the primer is worked well into the surface.

#### **DRYING TIMES**

- 10. As soon as it has become transparent, i.e. when the primer is tacky but not wet, the appropriate Bostik smoothing compound may be applied. Keep the area dust free until the smoothing compound is applied.
- 11. For best results, leave to dry for 12 hours. If the primed surface is left for longer than 24 hours, it may lose its tack and may require a repeat application.
- 12. Bostik GRIP E946 EPOXY will cure between 6 hours and

24 hours after application, depending on the substrate, temperature and ventilation. Under cold conditions, the curing rate will be considerably slower. The use of warm air blowers can assist curing.

Note: Fuel burning space heaters produce water vapour, which will increase humidity and extend curing times. Electric fans, where permissible are more effective.

#### **CLEANING**

 Clean tools and equipment with warm water immediately after use. Use white spirit if the material has dried.

#### **PRECAUTIONS IN USE**

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik GRIP E946 EPOXY, available at www.bostik.com/uk.

Smart help +44 (0) 1785 272625

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

 Sales
 Tel: 0844 371 1192
 Fax: 01785 241818
 customer.service@bostik.com

 Technical Advice
 Tel: 0844 371 1197
 Fax: 01785 272867
 technical.service@bostik.com

 Safety Data Sheets
 Tel: 01785 272625
 Fax: 01785 212962
 sds.box-eu@bostik.com